

TABLA DE EQUIVALENCIA DE CALIBRE Y ESPESOR GAUGE TO THICKNESS CHART

Espesor / Thickness		Acero Inoxidable	Galvanizado	Lámina de Acero	Aluminio
Calibre	Fracción	Stainless	Galvanized	Sheet Steel	Aluminium
Gauge	Fraction	in (mm)	in (mm)	in (mm)	in (mm)
30		0.0125 (0.33)	0.0157 (0.40)	0.0120 (0.30)	0.0100 (0.25)
29		0.0141 (0.36)	0.0172 (0.44)	0.0135 (0.34)	0.0113 (0.29)
28	1/64	0.0156 (0.41)	0.0187 (0.47)	0.0149 (0.38)	0.0126 (0.32)
27		0.0172 (0.43)	0.0202 (0.51)	0.0164 (0.42)	0.0142 (0.36)
26		0.0187 (0.48)	0.0217 (0.55)	0.0179 (0.45)	0.0159 (.40)
25		0.0219 (0.56)	0.0247 (0.63)	0.0209 (0.53)	0.0179 (0.46)
24		0.025 (0.64)	0.0276 (0.70)	0.0239 (0.61)	0.0201 (0.51)
23		0.0281 (0.71)	0.0306 (0.78)	0.0269 (0.68)	0.0226 (0.58)
22	1/32	0.0312 (0.79)	0.0336 (0.85)	0.0299 (0.76)	0.0253 (0.64)
21		0.0344 (0.86)	0.0366 (0.93)	0.0329 (0.84)	0.0285 (0.71)
20		0.0375 (0.95)	0.0396 (1.01)	0.0359 (0.91)	0.0320 (0.81)
19		0.0437 (1.1)	0.0456 (1.16)	0.0418 (1.06)	0.0359 (0.91)
18		0.0500 (1.27)	0.0516 (1.31)	0.0478 (1.21)	0.0403 (1.02)
17		0.0562 (1.4)	0.0575 (1.46)	0.0538 (1.37)	0.0453 (1.1)
16	1/16	0.0625 (1.59)	0.0635 (1.61)	0.0598 (1.52)	0.0508 (1.29)
15		0.0703 (1.8)	0.0710 (1.80)	0.0673 (1.71)	0.0571 (1.4)
14	5/64	0.0781 (1.98)	0.0785 (1.99)	0.0747 (1.90)	0.0641 (1.63)
13	3/32	0.094 (2.4)	0.0934 (2.37)	0.0897 (2.28)	0.072 (1.8)
12	7/64	0.1094 (2.78)	0.1084 (2.75)	0.1046 (2.66)	0.0808 (2.05)
11	1/8	0.1250 (3.18)	0.1233 (3.13)	0.1196 (3.04)	0.0907 (2.30)
10	9/64	0.1406 (3.57)	0.1382 (3.51)	0.1345 (3.42)	0.1019 (2.59)
9	5/32	0.1563 (3.97)	0.1532 (3.89)	0.1495 (3.80)	0.1144 (2.91)
8	11/64	0.1719 (4.37)	0.1681 (4.27)	0.1644 (4.18)	0.1285 (3.26)
7	3/16	0.1875 (4.76)		0.1793 (4.55)	0.1443 (3.67)
6	13/64	0.2031		0.1943 (4.94)	0.162 (4.1)
5	7/32	0.2187		0.2092 (5.31)	0.1819
4	15/64	0.2344		0.2242 (5.69)	0.2043
3	1/4	0.25		0.2391 (6.07)	0.2294